


You will be supported
by our technology,
resources and experience







Chemical-Resistant FKM

High Performance Rubber Material

- Applicable for use with many solvents
- General properties equivalent to standard FKM
- Offers superior abrasion resistance

Chemical Resistant FKM vs. Standard FKM



General Properties

	Chemical-resistant FKM	Standard FKM
	3301-70 (*1)	1320-75 (*1)
Hardness	74	73
Type A Durometer		
Tensile Strength / Mpa	20	13
Elongation / %	225	220
Compression Set / %	27	11
70 hours @ 200°C		
Abrasion Resistance(*2) / mm	0.4	1.9

*1:Material Number

*2 : Our evaluation method