



You will be supported
by our technology,
resources and experience



Heat-Resistant FKM

High Performance Rubber Material

- Heat resistance to over 200°C
- Excellent long-term compression set
- Lower weight loss



General Properties

		Heat-resistant FKM (3320-80 *1)	Standard FKM (1320-75*1)
Hardness			
Type A Durometer		77	73
Tensile Strength / Mpa		17	13
Elongation / %		220	220
Compression Set / %			
70 h @ 220°C		19	22
He Leak / Pa m ³ /sec	Original	2.3×10^{-8}	2.5×10^{-8}
	After 100h @150°C	2.3×10^{-8}	5.6×10^{-8}

*1:Material Number